



DIVERSIFIED
TESTING LABORATORIES, INC.
 WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
 P.O. BOX 4004
 BURLINGTON, NORTH CAROLINA 27215
 PHONE (336) 227-7710 • FAX (336) 227-1175
 www.diversifiedtestinglabs.com

January 28, 2020

Mr. Ray Misiti
 STRATAGLASS LLC
 2968 Ravenswood Road
 Suite 107
 Fort Lauderdale, FL 33312

Reference: Flammability Test Report
 Lab Identification No. 39913
 Invoice No. 71131

Dear Mr. Misiti:

One (1) sample, identified as **PANORAMA FR20 BY STRATAGLASS**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2019 Edition, (Test 1)". The results are as follows:

<u>Specimen Number</u>	<u>Test Results</u>	
	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	11.24
2	0.0	16.72
3	0.0	12.13
4	0.0	11.58
5	0.0	12.08
6	0.0	17.76
7	0.0	12.06
8	0.0	15.87
9	0.0	15.45
<u>10</u>	<u>0.0</u>	<u>12.22</u>
AVG	0.0	13.71

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

January 28, 2020

Mr. Ray Misiti
STRATAGLASS LLC
2968 Ravenswood Road
Suite 107
Fort Lauderdale, FL 33312

Reference: Flammability Test Report
Lab Identification No. 39913
Invoice No. 71131

Dear Mr. Misiti:

One (1) sample, identified as **PANORAMA FR20 BY STRATAGLASS**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2019 Edition, (Test 2, Folds Configuration)". The results are as follows:

Test Results

<u>Specimen Number</u>	<u>After Flame (seconds)</u>	<u>Residual Flame (seconds)</u>	<u>Char Length (inches)</u>
1	20.0	0.0	18.0
2	9.0	0.0	16.0
3	0.0	0.0	11.0
4	3.0	0.0	14.5

The fabric sample submitted **does not meet** the minimum requirements of the above standard. The length of char on the individual folded specimens shall not exceed 41.3 inches. Additionally, no specimen shall continue flaming for more than two (2) seconds after the test flame is removed and no residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

January 28, 2020

Mr. Ray Misiti
STRATAGLASS LLC
2968 Ravenswood Road
Suite 107
Fort Lauderdale, FL 33312

Reference: Flammability Test Report
Lab Identification No. 39913
Invoice No. 71131

Dear Mr. Misiti:

One (1) sample, identified as **PANORAMA FR20 BY STRATAGLASS**, was received and tested in accordance with the National Fire Protection Association No. 701, "Flame Propagation of Textiles and Films, 2019 Edition, (Test 2, Flat Configuration)". The results are as follows:

Test Results

<u>Specimen Number</u>	<u>After Flame</u> (seconds)	<u>Residual Flame</u> (seconds)	<u>Char Length</u> (inches)
1	0.0	4.0	15.0
2	0.0	4.0	13.5
3	0.0	3.0	14.0
4	0.0	0.0	14.0
5	0.0	0.0	15.0
6	0.0	0.0	14.0
7	0.0	0.0	13.5
8	0.0	0.0	15.0
9	0.0	0.0	15.0
10	0.0	0.0	14.0

The sample submitted **does not meet** the minimum requirements of the above standard. The length of char on the individual single flat specimens shall not exceed 17.1 inches. Additionally, no specimen shall continue flaming for more than two (2) seconds after the test flame is removed and no residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

